

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

Listing of Claims:

1. (Currently amended) A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s) ~~wherein the Lewis acid metal is from Groups 4, 5, 13, 14 or 15 of the Periodic Table~~, and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{3-n} wherein M is a Group 13 metal; each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals; n is an integer from 1 to 3; and each X is a halogen.
2. (Currently amended) The process of claim 28 [[1]], wherein the one or more hydrofluorocarbon(s) is represented by the formula: $C_xH_yF_z$ wherein x is an integer from 1 to 40 and y and z are integers of one or more.
3. (Original) The process of claim 2, wherein x is from 1 to 10.
4. (Original) The process of claim 2, wherein x is from 1 to 6.
5. (Original) The process of claim 2, wherein x is from 1 to 3.
6. (Currently amended) The process of claim 28 [[1]], wherein the one or more hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane; difluoromethane; trifluoromethane; fluoroethane; 1,1-difluoroethane; 1,2-difluoroethane; 1,1,1-trifluoroethane; 1,1,2-trifluoroethane; 1,1,1,2-

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

tetrafluoroethane; 1,1,2,2-tetrafluoroethane; 1,1,1,2,2-pentafluoroethane; 1-fluoropropane; 2-fluoropropane; 1,1-difluoropropane; 1,2-difluoropropane; 1,3-difluoropropane; 2,2-difluoropropane; 1,1,1-trifluoropropane; 1,1,2-trifluoropropane; 1,1,3-trifluoropropane; 1,2,2-trifluoropropane; 1,2,3-trifluoropropane; 1,1,1,2-tetrafluoropropane; 1,1,1,3-tetrafluoropropane; 1,1,2,2-tetrafluoropropane; 1,1,2,3-tetrafluoropropane; 1,1,3,3-tetrafluoropropane; 1,2,2,3-tetrafluoropropane; 1,1,1,2,2-pentafluoropropane; 1,1,1,2,3-pentafluoropropane; 1,1,1,3,3-pentafluoropropane; 1,1,2,2,3-pentafluoropropane; 1,1,2,3,3-pentafluoropropane; 1,1,1,2,3,3-hexafluoropropane; 1,1,1,2,3,3-hexafluoropropane; 1,1,1,3,3,3-hexafluoropropane; 1,1,1,2,2,3,3-heptafluoropropane; 1,1,1,2,3,3,3-heptafluoropropane; 1-fluorobutane; 2-fluorobutane; 1,1-difluorobutane; 1,2-difluorobutane; 1,3-difluorobutane; 1,4-difluorobutane; 2,2-difluorobutane; 2,3-difluorobutane; 1,1,1-trifluorobutane; 1,1,2-trifluorobutane; 1,1,3-trifluorobutane; 1,1,4-trifluorobutane; 1,2,2-trifluorobutane; 1,2,3-trifluorobutane; 1,3,3-trifluorobutane; 2,2,3-trifluorobutane; 1,1,1,2-tetrafluorobutane; 1,1,1,3-tetrafluorobutane; 1,1,1,4-tetrafluorobutane; 1,1,2,2-tetrafluorobutane; 1,1,2,3-tetrafluorobutane; 1,1,2,4-tetrafluorobutane; 1,1,3,3-tetrafluorobutane; 1,1,3,4-tetrafluorobutane; 1,1,4,4-tetrafluorobutane; 1,2,2,3-tetrafluorobutane; 1,2,2,4-tetrafluorobutane; 1,2,3,3-tetrafluorobutane; 1,2,3,4-tetrafluorobutane; 2,2,3,3-tetrafluorobutane; 1,1,1,2,2-pentafluorobutane; 1,1,1,2,3-pentafluorobutane; 1,1,1,2,4-pentafluorobutane; 1,1,1,3,3-pentafluorobutane; 1,1,1,3,4-pentafluorobutane; 1,1,1,4,4-pentafluorobutane; 1,1,2,2,3-pentafluorobutane; 1,1,2,2,4-pentafluorobutane; 1,1,2,3,3-pentafluorobutane; 1,1,2,4,4-pentafluorobutane; 1,1,3,3,4-pentafluorobutane; 1,2,2,3,3-pentafluorobutane; 1,2,2,3,4-pentafluorobutane; 1,1,1,2,2,3-hexafluorobutane; 1,1,1,2,2,4-hexafluorobutane; 1,1,1,2,3,3-hexafluorobutane; 1,1,1,2,3,4-hexafluorobutane; 1,1,1,2,4,4-hexafluorobutane; 1,1,1,3,3,4-hexafluorobutane; 1,1,1,3,4,4-hexafluorobutane; 1,1,1,4,4,4-hexafluorobutane; 1,1,2,2,3,3-hexafluorobutane; 1,1,2,2,3,4-hexafluorobutane; 1,1,2,2,4,4-hexafluorobutane; 1,1,2,3,3,4-hexafluorobutane; 1,1,2,3,4,4-hexafluorobutane; 1,2,2,3,3,4-hexafluorobutane; 1,1,1,2,2,3,3-heptafluorobutane; 1,1,1,2,2,4,4-heptafluorobutane; 1,1,1,2,2,3,4-heptafluorobutane; 1,1,1,2,3,3,4-

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

heptafluorobutane; 1,1,1,2,3,4,4-heptafluorobutane; 1,1,1,2,4,4,4-heptafluorobutane; 1,1,1,3,3,4,4-heptafluorobutane; 1,1,1,2,2,3,3,4-octafluorobutane; 1,1,1,2,2,3,4,4-octafluorobutane; 1,1,1,2,3,3,4,4-octafluorobutane; 1,1,1,2,2,4,4,4-octafluorobutane; 1,1,1,2,3,4,4,4-octafluorobutane; 1,1,1,2,2,3,3,4,4-nonafluorobutane; 1,1,1,2,2,3,4,4,4-nonafluorobutane; 1-fluoro-2-methylpropane; 1,1-difluoro-2-methylpropane; 1,3-difluoro-2-methylpropane; 1,1,1-trifluoro-2-methylpropane; 1,1,3-trifluoro-2-methylpropane; 1,3-difluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-methylpropane; 1,1,3-trifluoro-2-(fluoromethyl)propane; 1,1,1,3,3-pentafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2-(fluoromethyl)propane; fluorocyclobutane; 1,1-difluorocyclobutane; 1,2-difluorocyclobutane; 1,3-difluorocyclobutane; 1,1,2-trifluorocyclobutane; 1,1,3-trifluorocyclobutane; 1,2,3-trifluorocyclobutane; 1,1,2,2-tetrafluorocyclobutane; 1,1,3,3-tetrafluorocyclobutane; 1,1,2,2,3-pentafluorocyclobutane; 1,1,2,3,3-pentafluorocyclobutane; 1,1,2,2,3,3-hexafluorocyclobutane; 1,1,2,2,3,4-hexafluorocyclobutane; 1,1,2,3,3,4-hexafluorocyclobutane; 1,1,2,2,3,3,4-heptafluorocyclobutane; vinyl fluoride; 1,1-difluoroethene; 1,2-difluoroethene; 1,1,2-trifluoroethene; 1-fluoropropene; 1,1-difluoropropene; 1,2-difluoropropene; 1,3-difluoropropene; 2,3-difluoropropene; 3,3-difluoropropene; 1,1,2-trifluoropropene; 1,1,3-trifluoropropene; 1,2,3-trifluoropropene; 1,3,3-trifluoropropene; 2,3,3-trifluoropropene; 3,3,3-trifluoropropene; 1-fluoro-1-butene; 2-fluoro-1-butene; 3-fluoro-1-butene; 4-fluoro-1-butene; 1,1-difluoro-1-butene; 1,2-difluoro-1-butene; 1,3-difluoropropene; 1,4-difluoro-1-butene; 2,3-difluoro-1-butene; 2,4-difluoro-1-butene; 3,3-difluoro-1-butene; 3,4-difluoro-1-butene; 4,4-difluoro-1-butene; 1,1,2-trifluoro-1-butene; 1,1,3-trifluoro-1-butene; 1,1,4-trifluoro-1-butene; 1,2,3-trifluoro-1-butene; 1,2,4-trifluoro-1-butene; 1,3,3-trifluoro-1-butene; 1,3,4-trifluoro-1-butene; 1,4,4-trifluoro-1-butene; 2,3,3-trifluoro-1-butene; 2,3,4-trifluoro-1-butene; 2,4,4-trifluoro-1-butene; 3,3,4-trifluoro-1-butene; 3,4,4-trifluoro-1-butene; 4,4,4-trifluoro-1-butene; 1,1,2,3-tetrafluoro-1-butene; 1,1,2,4-tetrafluoro-1-butene; 1,1,3,3-tetrafluoro-1-butene; 1,1,3,4-tetrafluoro-1-butene; 1,1,4,4-tetrafluoro-1-butene; 1,2,3,3-tetrafluoro-1-butene;

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

1,2,3,4-tetrafluoro-1-butene; 1,2,4,4-tetrafluoro-1-butene; 1,3,3,4-tetrafluoro-1-butene; 1,3,4,4-tetrafluoro-1-butene; 1,4,4,4-tetrafluoro-1-butene; 2,3,3,4-tetrafluoro-1-butene; 2,3,4,4-tetrafluoro-1-butene; 2,4,4,4-tetrafluoro-1-butene; 3,3,4,4-tetrafluoro-1-butene; 3,4,4,4-tetrafluoro-1-butene; 1,1,2,3,3-pentafluoro-1-butene; 1,1,2,3,4-pentafluoro-1-butene; 1,1,2,4,4-pentafluoro-1-butene; 1,1,3,3,4-pentafluoro-1-butene; 1,1,3,4,4-pentafluoro-1-butene; 1,1,4,4,4-pentafluoro-1-butene; 1,2,3,3,4-pentafluoro-1-butene; 1,2,3,4,4-pentafluoro-1-butene; 1,2,4,4,4-pentafluoro-1-butene; 2,3,3,4,4-pentafluoro-1-butene; 2,3,4,4,4-pentafluoro-1-butene; 3,3,4,4,4-pentafluoro-1-butene; 1,1,2,3,3,4-hexafluoro-1-butene; 1,1,2,3,4,4-hexafluoro-1-butene; 1,1,2,4,4,4-hexafluoro-1-butene; 1,2,3,3,4,4-hexafluoro-1-butene; 1,2,3,4,4,4-hexafluoro-1-butene; 2,3,3,4,4,4-hexafluoro-1-butene; 1,1,2,3,3,4,4-heptafluoro-1-butene; 1,1,2,3,4,4,4-heptafluoro-1-butene; 1,1,3,3,4,4,4-heptafluoro-1-butene; 1,2,3,3,4,4,4-heptafluoro-1-butene; 1-fluoro-2-butene; 2-fluoro-2-butene; 1,1-difluoro-2-butene; 1,2-difluoro-2-butene; 1,3-difluoro-2-butene; 1,4-difluoro-2-butene; 2,3-difluoro-2-butene; 1,1,1-trifluoro-2-butene; 1,1,2-trifluoro-2-butene; 1,1,3-trifluoro-2-butene; 1,1,4-trifluoro-2-butene; 1,2,3-trifluoro-2-butene; 1,2,4-trifluoro-2-butene; 1,1,1,2-tetrafluoro-2-butene; 1,1,1,3-tetrafluoro-2-butene; 1,1,1,4-tetrafluoro-2-butene; 1,1,2,3-tetrafluoro-2-butene; 1,1,2,4-tetrafluoro-2-butene; 1,2,3,4-tetrafluoro-2-butene; 1,1,1,2,3-pentafluoro-2-butene; 1,1,1,2,4-pentafluoro-2-butene; 1,1,1,3,4-pentafluoro-2-butene; 1,1,1,4,4-pentafluoro-2-butene; 1,1,2,3,4-pentafluoro-2-butene; 1,1,2,4,4-pentafluoro-2-butene; 1,1,1,2,3,4-hexafluoro-2-butene; 1,1,1,2,4,4-hexafluoro-2-butene; 1,1,1,3,4,4-hexafluoro-2-butene; 1,1,1,4,4,4-hexafluoro-2-butene; 1,1,2,3,4,4-hexafluoro-2-butene; 1,1,1,2,3,4,4-heptafluoro-2-butene; 1,1,1,2,4,4,4-heptafluoro-2-butene; and mixtures thereof.

7. (Currently amended) The process of claim 28 [[1]], wherein the one or more hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane, difluoromethane, trifluoromethane, 1,1-difluoroethane, 1,1,1-trifluoroethane, 1,1,1,2-tetrafluoroethane, and mixtures thereof.

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

8. (Canceled)
9. (Original) The process of claim 1, wherein the diluent comprises from 20 to 100 volume % HFC based upon the total volume of the diluent.
10. (Original) The process of claim 1, wherein the diluent comprises from 25 to 100 volume % HFC based upon the total volume of the diluent.
11. (Currently amended) The process of claim 28 [[1]], wherein the diluent further comprises a hydrocarbon, a non-reactive olefin, and/or an inert gas.
12. (Currently amended) The process of claim 28 [[1]], wherein the diluent further comprises a halogenated hydrocarbon other than an HFC.
13. (Currently amended) The process of claim 28 [[1]], wherein the diluent further comprises methyl chloride.
14. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is represented by the formula MX_4 ;
wherein M is a Group 4, 5, or 14 metal; and
each X is a halogen.
15. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{4-n} ;
wherein M is Group 4, 5, or 14 metal;
each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 4; and
each X is a halogen.

2003B133A
1st OA dated 9/30/06
Response dated 11/30/06

16. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is represented by the formula $M(RO)_nR'_mX_{4-(m+n)}$; wherein M is Group 4, 5, or 14 metal; each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals; each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals; n is an integer from 0 to 4; m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and each X is a halogen.
17. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is represented by the formula $M(RC=OO)_nR'_mX_{4-(m+n)}$; wherein M is Group 4, 5, or 14 metal; each $RC=OO$ is a monovalent C_2 to C_{30} hydrocarbacyl radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals; each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals; n is an integer from 0 to 4; m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and each X is a halogen.
18. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is represented by the formula MOX_3 ; wherein M is a Group 5 metal; and each X is a halogen.
19. (Canceled)

2003B133A

1st OA.dated 9/30/06

Response dated 11/30/06

20. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is represented by the formula $M(RO)_nR'_mX_{3-(m+n)}$;
 wherein M is a Group 13 metal;
 each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;
 each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 3;
 m is an integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and
 each X is a halogen.
21. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is represented by the formula $M(RC=OO)_nR'_mX_{3-(m+n)}$;
 wherein M is a Group 13 metal;
 each $RC=OO$ is a monovalent C_2 to C_{30} hydrocarbacyl radical independently selected from the group independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;
 each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 3;
 m is a integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and
 each X is a halogen.
22. (Currently amended) ~~The process of claim 1, A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the one or more Lewis acid(s) is represented by the formula MX_y ;~~

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

wherein M is a Group 15 metal;

each X is a halogen; and

y is 3, 4 or 5.

23. (Currently amended) ~~The process of claim 1;~~ A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the one or more Lewis acid(s) is represented by the formula MR_nX_{y-n} ;
wherein M is a Group 15 metal;
each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 4;
 y is 3, 4 or 5, wherein n is less than y ; and
each X is a halogen.
24. (Currently amended) ~~The process of claim 1;~~ A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the one or more Lewis acid(s) is represented by the formula $M(RO)_nR'_mX_{y-(m+n)}$;
wherein M is a Group 15 metal,
each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;
each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y ; and

each X is a halogen.

25. (Currently amended) ~~The process of claim 1,~~ A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the one or more Lewis acid(s) is represented by the formula $M(RC=OO)_nR'_mX_{y-(m+n)}$;

wherein M is a Group 15 metal;

each RC=OO is a monovalent C₂ to C₃₀ hydrocarbacyloxy radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y ; and

each X is a halogen.

26. (Currently amended) The process of claim 28 [[1]], wherein the one or more Lewis acid(s) is independently selected from the group consisting of titanium tetrachloride, titanium tetrabromide, vanadium tetrachloride, tin tetrachloride, zirconium tetrachloride, titanium bromide trichloride, titanium dibromide dichloride, vanadium bromide trichloride, tin chloride trifluoride, benzyltitanium trichloride, dibenzyltitanium dichloride, benzylzirconium trichloride, dibenzylzirconium dibromide, methyltitanium trichloride, dimethyltitanium difluoride, dimethyltin

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

28. (Currently amended) ~~The process of claim 1,~~ A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s) wherein the Lewis acid metal is from Groups 4, 5, 13, 14 or 15 of the Periodic Table, and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the process further comprises one or more initiator(s) [[is]] independently selected from the group consisting of a hydrogen halide, a carboxylic acid, a carboxylic acid halide, a sulfonic acid, an alcohol, a phenol, a polymeric halide, a tertiary alkyl halide, a tertiary aralkyl halide, a tertiary alkyl ester, a tertiary aralkyl ester, a tertiary alkyl ether, a tertiary aralkyl ether, an alkyl halide, an aryl halide, an alkylaryl halide and an arylalkylacid halide.
29. (Currently amended) ~~The process of claim 1,~~ A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s) wherein the Lewis acid metal is from Groups 4, 5, 13, 14 or 15 of the Periodic Table, and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the process further comprises one or more initiator(s) [[is]] independently selected from the group consisting of HCl, H₂O, methanol, (CH₃)₃CCl, C₆H₅C(CH₃)₂Cl, (2-Chloro-2,4,4-trimethylpentane) and 2-chloro-2-methylpropane.
30. (Currently amended) ~~The process of claim 1,~~ A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s) wherein the Lewis acid metal is from Groups 4, 5, 13, 14 or 15 of the Periodic Table, and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

above 0 to 14,000 kPa and wherein the process further comprises one or more initiator(s) ~~[[is]]~~ independently selected from the group consisting of hydrogen chloride, hydrogen bromide, hydrogen iodide, acetic acid, propanoic acid, butanoic acid; cinnamic acid, benzoic acid, 1-chloroacetic acid, dichloroacetic acid, trichloroacetic acid, trifluoroacetic acid, p-chlorobenzoic acid, p-fluorobenzoic acid, acetyl chloride, acetyl bromide, cinnamyl chloride, benzoyl chloride, benzoyl bromide, trichloroacetylchloride, trifluoroacetylchloride, p-fluorobenzoylchloride, methanesulfonic acid, trifluoromethanesulfonic acid, trichloromethanesulfonic acid, p-toluenesulfonic acid, methanesulfonyl chloride, methanesulfonyl bromide, trichloromethanesulfonyl chloride, trifluoromethanesulfonyl chloride, p-toluenesulfonyl chloride, methanol, ethanol, propanol, 2-propanol, 2-methylpropan-2-ol, cyclohexanol, benzyl alcohol, phenol, 2-methylphenol, 2,6-dimethylphenol, p-chlorophenol, p-fluorophenol, 2,3,4,5,6-pentafluorophenol, and 2-hydroxynaphthalene.

31. (Currently amended) ~~The process of claim 1,~~ A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s) wherein the Lewis acid metal is from Groups 4, 5, 13, 14 or 15 of the Periodic Table, and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the process further comprises one or more initiator(s) ~~[[is]]~~ independently selected from the group consisting of 2-chloro-2,4,4-trimethylpentane; 2-bromo-2,4,4-trimethylpentane; 2-chloro-2-methylpropane; 2-bromo-2-methylpropane; 2-chloro-2,4,4,6,6-pentamethylheptane; 2-bromo-2,4,4,6,6-pentamethylheptane; 1-chloro-1-methylethylbenzene; 1-chloroadamantane; 1-chloroethylbenzene; 1, 4-bis(1-chloro-1-methylethyl) benzene; 5-tert-butyl-1,3-bis(1-chloro-1-methylethyl) benzene; 2-acetoxy-2,4,4-trimethylpentane; 2-benzoyloxy-2,4,4-trimethylpentane; 2-acetoxy-2-methylpropane; 2-benzoyloxy-2-methylpropane; 2-acetoxy-2,4,4,6,6-pentamethylheptane; 2-benzoyl-2,4,4,6,6-pentamethylheptane; 1-

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

acetoxy-1-methylethylbenzene; 1-acetoxyadamantane; 1-benzoyloxyethylbenzene; 1,4-bis(1-acetoxy-1-methylethyl) benzene; 5-tert-butyl-1,3-bis(1-acetoxy-1-methylethyl) benzene; 2-methoxy-2,4,4-trimethylpentane; 2-isopropoxy-2,4,4-trimethylpentane; 2-methoxy-2-methylpropane; 2-benzyloxy-2-methylpropane; 2-methoxy-2,4,4,6,6-pentamethylheptane; 2-isopropoxy-2,4,4,6,6-pentamethylheptane; 1-methoxy-1-methylethylbenzene; 1-methoxyadamantane; 1-methoxyethylbenzene; 1,4-bis(1-methoxy-1-methylethyl) benzene; 5-tert-butyl-1,3-bis(1-methoxy-1-methylethyl) benzene, and 1,3,5-tris(1-chloro-1-methylethyl) benzene.

32. (Currently amended) The process of claim 1, A polymerization process comprising contacting one or more monomer(s), one or more Lewis acid(s) wherein the Lewis acid metal is from Groups 4, 5, 13, 14 or 15 of the Periodic Table, and a diluent comprising one or more hydrofluorocarbon(s) (HFC's) in a reactor and wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above 0 to 14,000 kPa and wherein the process further comprises a weakly-coordinating anion.
33. (Currently amended) The process of claim 28 [[1]], wherein the process is substantially absent of water.
34. (Currently amended) The process of claim 28 [[1]], wherein the ~~process further comprises one or more initiator(s) comprise greater than 30 ppm water (based upon weight).~~
35. (Currently amended) The process of claim 28 [[1]], wherein the one or more monomer(s) is independently selected from the group consisting of olefins, alpha-olefins, disubstituted olefins, isoolefins, conjugated dienes, non-conjugated dienes, styrenics, substituted styrenics, and vinyl ethers.

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

36. (Currently amended) The process of claim 28 [[1]], wherein the one or more monomer(s) is independently selected from the group consisting of styrene, para-alkylstyrene, para-methylstyrene, alpha-methyl styrene, divinylbenzene, diisopropenylbenzene, isobutylene, 2-methyl-1-butene, 3-methyl-1-butene, 2-methyl-2-pentene, isoprene, butadiene, 2,3-dimethyl-1,3-butadiene, β -pinene, myrcene, 6,6-dimethyl-fulvene, hexadiene, cyclopentadiene, methyl cyclopentadiene, piperylene, methyl vinyl ether, ethyl vinyl ether, and isobutyl vinyl ether.
37. (Currently amended) The process of claim 28 [[1]], wherein the reactor is independently selected from the group consisting of a continuous flow stirred tank reactor, a plug flow reactor, a moving belt or drum reactor, a jet or nozzle reactor, a tubular reactor, a batch reactor, and an autorefrigerated boiling-pool reactor.
38. (Currently amended) The process of claim 28 [[1]] wherein the diluent has a dielectric constant greater than 10 at -85°C .
39. (Original) The process of claim 38, wherein the dielectric constant is greater than 20 at -85°C .
40. (Original) The process of claim 39, wherein the dielectric constant is greater than 25 at -85°C .
41. (Original) The process of claim 40, wherein the dielectric constant is greater than 40 at -85°C .
42. (Currently amended) The process of claim 28 [[1]], wherein the process forms a polymer having a diluent mass uptake of less than 4 wt%.
43. (Original) The process of claim 42, wherein the polymer has a diluent mass uptake of less than 3 wt%.

2003B133A
1st OA dated 9/30/06
Response dated 11/30/06

44. (Original) The process of claim 43, wherein the polymer has a diluent mass uptake of less than 2 wt%.
45. (Original) The process of claim 44, wherein the polymer has a diluent mass uptake of less than 1 wt%.
46. (Original) The process of claim 45, wherein the polymer has a diluent mass uptake of less than 0.5 wt%.
47. (Currently amended) The polymerization process of claim 28[[1]], the diluent comprising methyl chloride and one or more hydrofluorocarbon(s) independently selected from the group consisting of difluoromethane, 1,1-difluoroethane, and 1,1,1,2-tetrafluoroethane in a reactor.
48. (Original) The process of claim 47, wherein the diluent further comprises a non-reactive olefin, and/or an inert gas.
49. (Currently amended). The polymerization process of claim 28[[1]], the process comprising the steps of:
reacting the one or more monomer(s) in the presence of one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's); and
withdrawing the polymer from the reactor.
50. (Currently amended) The polymerization process of claim 28[[1]], the process comprising the steps of:
(a) introducing one or more monomer(s) into a reactor;
(b) adding one or more Lewis acid(s) and one or more initiator(s);

2003B133A

1st OA dated 9/30/06

Response dated 11/30/06

- (c) introducing a diluent comprising one or more hydrofluorocarbon(s) (HFC's);
and
- (d) withdrawing a polymer from the reactor.
51. (Currently amended) The polymerization process of claim 28 [[1]] in which particles of polymer are produced in a slurry using a catalyst system and a diluent comprising one or more hydrofluorocarbon(s) (HFC's).
52. (Canceled)
53. (Currently amended) A polymerization medium suitable to polymerize one or more monomer(s) to form a polymer, the polymerization medium comprising one or more Lewis acid(s), one or more initiator(s) and a diluent comprising one or more hydrofluorocarbon(s) (HFC); wherein the one or more Lewis acid(s) is not a compound represented by formula MX_3 , where M is a group 13 metal and X is a halogen, wherein the diluent comprises from 5 to 100 volume % HFC based upon the total volume of diluent, the temperature of the polymerization is less than 0°C and the pressure is from above [00148] 0 to 14,000 kPa, and wherein the one or more initiator(s) is independently selected from the group consisting of a hydrogen halide, a carboxylic acid, a carboxylic acid halide, a sulfonic acid, an alcohol, a phenol, a polymeric halide, a tertiary alkyl halide, a tertiary aralkyl halide, a tertiary alkyl ester, a tertiary aralkyl ester, a tertiary alkyl ether, a tertiary aralkyl ether, an alkyl halide, an aryl halide, an alkylaryl halide and an arylalkylacid halide.

Claims 54-58 (Canceled)

59. (Currently amended) A process to polymerize one or more monomer(s) to form a polymer, comprising contacting one or more monomer(s) in a [the] polymerization medium comprising one or more Lewis acid(s), a weakly coordinating anion, and a diluent comprising one or more hydrofluorocarbon(s) (HFC); wherein the one or more

